

GroupCode :

TS-608

【Physical Properties Data】

Item	Unit	Value	Test Method
Specific Gravity	-	1.4	JIS K 7112 (MOD ISO1183)
Surface Hardness (Rockwell)	M scale	71	JIS K 7202
	R scale	122	
Tensile Stress at Yield	MPa	75	JIS K 7161-2-1B/50 (IDT ISO527-2)
Nominal Tensile Strain at Break	%	9	
Modulus of Elasticity in Tension	MPa	3300	JIS K 7161-2-1B/1 (IDT ISO527-2)
Charpy Impact Strength(Notched)	kJ/m ²	2	JIS K 7111-1epA (MOD ISO179)
Flexural Stress	MPa	104	JIS K 7171 (MOD ISO178)
Flexural Modulus	MPa	3300	
Temperature of Deflection under Load	°C(0.45MPa)	-	JIS K 7191
	°C(1.80MPa)	66	
Vicat Softening Temperature	°C(methodA/10N)	-	JIS K 7206 (MOD ISO306)
	°C(methodB/50N)	71	
Dimensional Change on Heating (145°C/55min)	%(longitudinal)	-3	JIS K 7133 (IDT ISO11501)
	%(latitudinal)	-1	
Surface Resistivity	10 ^X Ω/□	>15	JIS K 6911
Volume Resistivity	10 ^X Ω•m	>13	
Total light transmittance	%	76/72/65	JIS K 7161-1

【Other】

20mm/30mm/40mm

Item	Unit	Value	test method
Color	-	Transparent	-
Munsell No.	-	-	-

The above data are a series of test results with 5mm thick specimen and given here without guarantee.