

	FM Standard Plates		FM Heat-Resistant Plates			FM Static-Dissipative Plates	FM Heat-Resistant and Static-Dissipative Plates	Testing Methods
	Continuous Press (FMET) Press lamination (FMET-)	Continuous Press	Press lamination			Continuous Press	Press lamination	
	FMET4323 FMET4773	FMRTS4605	FMH5305	FMH5775	FMHS6650	FMND74602	FMND7605	
	1.45	1.40	1.55	1.58	1.46	1.40	1.46	ISO 1183-1 and -2
	67	76	80	79	83	76	86	JIS K 7202
	118	120	123	121	123	121	124	
	58	68	63	64	74	68	72	JIS K 7161-2-1B/50
	13	9	20	28	12	8	14	
	2900	3100	3000	2900	3300	3100	3000	JIS K 7161-2-1B/1
	3.8	1.6	7.2	5.0	1.6	1.6	1.7	JIS K 7111-1 1epA
	78	87	88	84	99	87	93	JIS K 7171
	2900	3100	3000	2900	3300	3100	3000	
	72	92	82	83	86	92	86	JIS K 7181-B/5
	2600	2600	2500	2500	2500	2600	2500	JIS K 7181-A/1
	60	64	69	69	68	63	68	JIS K 7214
	73	63	86	94	85	63	85	JIS K 7191
	81	71	97	106	94	71	94	JIS K 7206
	−2* ³	−3	−4	−4	−5	−3	−5	JIS K 6745
	−1* ³	−1	−1	−1	1	−1	1	
	6.7	6.4	6.5	6.5	6.1	6.4	6.1	JIS K 7197
	0.24	0.21	0.21	0.19	0.16	0.21	0.16	Laser flash method
	1.27	1.12	1.24	1.05	1.06	1.12	1.06	JIS K 7123
	Self-extinguishing							JIS K 6911
	10 ¹⁵ or more					10 ^{6~9}		JIS K 6911
	10 ¹³ or more							JIS K 6911
	22	18	23	18	20	18	20	JIS K 6911
	3	3	3	3	3	3	3	JIS K 6911
	0.025	0.012	0.015	0.010	0.012	0.012	0.012	JIS K 6911
	0.018	0.010	0.025	0.023	0.012	0.011	0.012	JIS K 7209
	–	78	–	–	71	75	63	JIS K 7361-1
	Ivory white	Transparent	Ivory	White	Transparent	Transparent	Transparent	–